



Flex-R, Sandswood House,  
Hillbottom Road, Sands Industrial Estate,  
High Wycombe, Buckinghamshire, HP12 4HJ  
Tel: 01494 448792  
Email: [enq@flex-r.co.uk](mailto:enq@flex-r.co.uk)  
Web: [www.flex-r.co.uk](http://www.flex-r.co.uk)



## Reinforcing Fabric

A non-woven, spun-bound, polypropylene reinforced fabric

## Description

ClassicLiquid Reinforcing Fabric is a non-woven, spun-bound, polypropylene reinforced fabric.

## Recommended For

For use when applying ClassicLiquid Waterproofing over existing Built-Up Felt and Asphalt Roofs.

## Application Procedure

ClassicLiquid Reinforcing Fabric is applied between two coats of ClassicLiquid Waterproof Coating.

Can be used in the following conditions:

- ◆ Temperature Range: 5-35°C
- ◆ Relative Humidity: <85%

## Packaging and Shelf Life

ClassicLiquid Reinforcing Fabric is supplied in white rolls 25m x 1m

## Storage

ClassicLiquid Reinforcing Fabric must be kept in a cool and dry place, at temperatures of between 5-25°C.

- ◆ Made of 100% polypropylene material at high temperature and spun-bound
- ◆ Non-toxic, non-irritant
- ◆ Made from materials conforming to FDA Standard requirements
- ◆ No other chemical composition, stable, non-toxic, no smell, safe for sensitive skin

## Safety

ClassicLiquid Reinforcing Fabric is a non-hazardous material.

## Technical Specification

Material	100% Polypropylene
Colour	White
Technology	Spunbound

	UNIT	CLASSICLIQUID REINFORCING FABRIC	
Weight	g/sq.m	50	
Colour		White	
Thickness	Mm	0.38	
Tensile Strength	n/5cm	MD	104
		CD	89
Elongation	%	MD	70
		CD	80

Certified quality, environmental and occupational health & safety management systems:  
ISO 9001/14001 & OHSAS 18001.

